RG104 E-1 Box 121

1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.		Assay No.	Name of Depositor.	Weight before Melting. oz.	dec.	Weight after Melting. oz.	dec.	Loss. oz.	dec.	Loss per ct.		Gain. oz.	dec.	Description of Bullion.
April	26th	699	G. C. Thompson	37	95	34	92	3	03	7	97			Jewelry, Wat. Cases, Bars &c.
		700	Do	8	93	8	86		07		67			Button
		1	B. Metzger	10	15	8	30	1	85	18	50			Button, Base
		2	Wm. H. Lee	84	50	84	44		06		07			Bar
		3	Do	12	26	12	25		01		08			Buttons
		4	J. C. Meeks	26	86	26	86							U.S. Coin
	27th	5	N. C. Gray	42	15	35	55	6	60	15	71			Button, Base
		6	G. C. Thompson	6	45	6	42		03		50			Button & Piece
		7	C. Nehl	12	76	12	50		26	2	00			Grs, Dakota & Spec., Montana
		8	A. Levy	24	87	24	85		02		08			Bar
		9	Phillips & Jacobs	53	78	53	73							U.S. Coin
		10	Brecht, Bickel & Brecht	5	11	5	05		06	1	20			Grs. Dakota
		1	Richd Nelms	26	86	26	86							U.S. Coin
	28th	2	Simons, Bro. & Co.	80	82	80	80		02		03			Bars
		3	A. Hernbert	46	22	46	20		02		04			Bar
	29th	4	G. C. Thompson	13	86	9	89	3	97	28	36			Jewelry, Wat. Cases & Rings &c.
		5	Do	47	87	46	19	1	68	3	50			Ring & Silver
		6	A. Loudon Snowden, Supt.	125	26	125	23		03		02			Bars & Pieces, N.C. Mint
	30th	7	G. C. Thompson	7	61	7	62						01	Bar & Lump, Va.
May	1st	8	H. Muhr's Sons	16	35	16	34		01		06			Bar
		9	G. C. Thompson	6	02	6	02							Bar, Col.
		20	Chas. A. Jones	23	25	18	85	4	40	19	13			Leaf
		1	Carrow, Bishop & Co.	36	55	19	22	17	13	47	55			Bars, Base
		2	G. C. Thompson	30	96	27	35	3	61	11	65			Wat. Cases, Jewelry, &c.
		3	J. C. White, Bennett 19.91	20	43	19	86		57	2	85			D.F.C., Fillings, &c.
		4	Phillips & Jacobs	53	70	53	70							U.S. Coin
				861	25	817	86	43	43	6	36		01	

Notes of Melter & Refiner. 6/5/80

The deposits are from the following sources:

Dacotah &c.		2
Virginia	(1)	1
N. Carolina	(1)	1
Colorado	(1)	1
Finer bullion	(3)	8
Base &, Dent plate		2
Jewelry &c		2
Very base		5
Coin		4
Total		26

The loss on the finer bullion, 0.14 %, is very moderate, considering that two of them belong to the variable nondescript "button", which lost about .58 %. The loss on the baser bullion, 3.17 %, is low; — on the jewelry, 9.81 %, is about the general medium; — on the very base bullion 25.86 %, is a legitimate average.

J. C. Booth
M&R.

For week ending May 1st 1880
Approximate value, $ 12,677.50

To the Director of the Mint.

J. Holley Bayliss, Register.

RG104 E-1 Box 121

Report of Gold Deposits melted for week ending May 1st 1880.

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending May 1, 1880.

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]